

ProRox® PS 210

ProRox PS 210 is a mandrel wound stone wool pipe section. The highly durable insulation sections are supplied split and hinged for easy snap-on assembly and are especially suitable for thermal insulation of industrial pipe work.



Product properties in accordance with ASTM C547

	Performance								Norms
Thermal conductivity at mean temperature	T_m (°F)	100	200	300	400	500	600	700	ASTM C335
	λ (BTU.in/hr.ft ² .°F)	0.25	0.31	0.37	0.45	0.54	0.65	0.77	
Maximum use temperature	1.200°F (649°C)								ASTM C447
Sag resistance	≤ 5% at 1.200°F (649°C)								ASTM C411
Linear shrinkage	≤ 2% at 1.200°F (649°C)								ASTM C356
Surface burning characteristics	Flame spread index - Passed; Smoke development index - Passed								ASTM E84
Corrosion resistance	Evaluation on external stress corrosion cracking tendency of austenitic stainless steel = Passed								ASTM C692 / ASTM C795
	Chemical analysis for Cl ⁻ , Fl ⁻ , Na ⁺ , SiO ₄ ⁴⁻ : Results fall within acceptability limits of ASTM C795								ASTM C871 / ASTM C795
Vapor sorption	≤ 5%w/w								ASTM C1104
Compliance	ASTM C547 Type I, II, IV								

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or application conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

®/TM: US - owner ROCKWOOL International A/S used under license; Canada owner Roxul Inc.